



PRODUCT DATA SHEET

# 9130 TRUCK BEDLINER

**PRODUCT DESCRIPTION:**

A 2K protective coating designed for long-lasting and highly durable paint applications on truck bedliners (e.g., pickup trucks) or other heavily stressed surfaces of vehicles. It is suitable for use as underbody protection. With excellent adhesion, it provides robust protection against stains, rust, and mechanical damage as well as the added benefits of vibration and noise reduction. The product can be conveniently applied using an under-seal spray gun directly from the container.

Available in Black and Tintable version.

**SUBSTRATES:**

Polyester putties, Fiberglass, 2K acrylic primers, all metallic surfaces, plastics.

**Notes:** For maximum adhesion and anticorrosive properties on bare metals, it is recommended prior use of Vollchem 9330 Epoxy Primer, or Vollchem 9350 Wash Primer or Vollchem 9352 1K Etch Primer. For maximum adhesion on plastics, it is recommended to sand with P100 - P180 grit papers followed by the application of 9355 1K Plastic Primer.

**SUBSTRATE PREPARATION:**



Surfaces must be clean, dry, and free of rust, dust, and grease. Before the application use 9651 Degreaser.

**APPLICATION:**



Always wear protective equipment



3 parts 9130 BLACK  
1 part 9551



3 parts 9130 Tintable  
1 part 9551  
Add 10% of 2K Acrylic Paint or Solventborne Basecoat Paint in part A. Mix with hardener (part B) and allow to stand for 10 min / 23°C (73°F)



After mixing shake well for 2 - 3 min  
Pot life: 1.5 h / 23°C (73°F)



Standard or coarser texture use with UBS gun. UBS Nozzle 4 - 5 mm  
- 3 - 4 bar (44 - 58 psi)  
- Distance from object 50 cm  
- 2 coats with an even sweeping motion (30 minutes between coats at 23°C)  
1st coat even sweeping motion,  
2nd coat reduce pressure 1.5 bar (22 psi) dropping over the first coat.



Standard finer texture with normal gravity spray gun (1.6 - 2.0 mm)  
- Add 10% thinner / reducer Vollchem 9612  
- 2 bar (29 psi)  
- Distance from object 20 cm  
- 2 coats with an even sweeping motion as wet on wet application (30 minutes between coats at 23°C)



20 min / 23 °C (32°F)

PRODUCT DATA SHEET

# 9130 TRUCK BEDLINER



Force Dry 30 min / 60°C (140°F)  
Light duty 1 - 2 days  
Fully cured 3 - 4 days

Air Non force dry / 23°C (73°F)  
Touch free 1 h  
Light duty 2 - 3 days  
Fully cured 5 - 7 days



Close container tightly

#### **EQUIPMENT CLEANING:**

After use, clean all equipment thoroughly with Nitro Thinner.

#### **TYPICAL PRODUCT DATA:**

**SPECIFIC GRAVITY:** 1.27+0.03g/cm<sup>3</sup>

**SOLIDS CONTENT:** 75+-2%

**THEORETICAL COVERAGE:** 3 m<sup>2</sup> / l at (2 coats applied with UBS gun)

**VOC INFORMATION:** 2004/42/IIB(e) (840)840

**COLOUR:** BLACK, TINTABLE

**PACKSIZE:** 0.6L

**STORAGE CONDITIONS:** Store tightly closed in a dry and cool place (5°- 25°C).

Protect from freeze, heat and direct exposure to sunlight.

**SHELF LIFE:** 24 months in tightly closed containers

For professional use only! These products are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps to ensure the suitability of the product for the intended purpose. We are not liable for its correctness, accuracy and completeness.

All rights reserved. The user of this product should use the product in accordance with the laws and regulations for safety at work and waste management. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

JUNE 2023